

## PRODUCT DESCRIPTION

The BF PRINT GLITTER series consists of three polyurethane films with a glitter finish available in three different basic colors: **white**, **silver** and **gold**. The finish of this film makes the print bright and shiny thanks to the glitter effect, while keeping it smooth to the touch.

BF PRINT GLITTER is free of PVC, plasticizers, and heavy metals. They are compatible with solvent, Eco-solvent, and Latex inks.

The adhesive polyester carrier guarantees perfect stability during the printing phases. After cutting and weeding, the product can be placed on the garment by transferring it with the BF MYLAR, which must then be removed right after pressing, while still hot. It is recommended to let the print dry for at least 8 hours before proceeding with cutting and application.

## APPLICATION STEPS

- Print - do not mirror
- Cut - 45° blade
- Weed excess material
- Apply BF MYLAR - remove air bubbles
- Remove from liner
- Turn on your heat press - heat to 150°C/305°F
- Place your graphic on the shirt
- Press it - 150°C/305°F for 10 seconds
- Remove BF MYLAR - hot

## SIZES

**H 50 cm** L 25 mt / 12,5mt / 5 mt

**H 75 cm** L 25 mt (upon request)

**H 100 cm** L 25 mt (upon request)

**H 150 cm** L 25 mt (upon request)

Comply with  
regulation **REACH**  
n°1907/2006/EU

## SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

Rev\_2021/03

## TECHNICAL DATA



Film: PU/Polyurethane



Thickness: 100μ (±5%)



Liner: adhesive PET



Finish: glossy



Inks: solvent, eco-solvent, latex

## PLOTTER SETTING



Cut settings: do not mirror



Blade: 45°



Minimum cut: 0,5 cm

## APPLICATION



Temperature: 150°C - 305°F



Time: 10"



Liner removal: hot



Pressure: medium - 3,5 bar - 50 PSI



Textile: organic, synthetic, mixed

## WASH RESISTANCE

First wash after application wait 12 hours

Max wash temperature\* 40°C - 104°F

Dry clean ✗

Dryer ✗

\*Temperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

follow us

HEADQUARTERS B-FLEX ITALIA S.r.l. info@b-flexitalia.com | www.b-flexitalia.com


NORTH AMERICA BRANCH B-FLEX AMERICA LLC info@b-flexamerica.com | www.b-flexamerica.com

ASIA-PACIFIC BRANCH B-FLEX PACIFIC PTY LTD info@b-flexpacific.com | www.b-flexpacific.com







**BF PRINTGLITTER**  
**PRINT&CUT**



**BF PRINTGW**  
WHITE GLITTER GLOSSY 100MY



**BF PRINTGG**  
GOLD GLITTER GLOSSY 100MY



**BF PRINTGS**  
SILVER GLITTER GLOSSY 100MY



- Extra glossy effect
- Available in three different colors
- Easy to work