

PRODUCT DESCRIPTION

BF PRINTOLD is a polyurethane block-out film, printable with solvent, eco-solvent and latex inks. It is suitable for heat transfer on cotton fabrics, polyester and acrylic garments and gives a vintage finishing after washing.

BF PRINTOLD is ideal to be pressed on heavy fabrics like sweatshirts and hoodies.

APPLICATION STEPS

- Print - do not mirror
- Cut - 45° blade
- Weed excess material
- Apply BF MYLAR - remove air bubbles
- Remove from liner
- Turn on your heat press - heat to 145°C/295°F
- Place your graphic on the shirt
- Press it - 145°C/295°F for 12 seconds
- Wait 6/7 seconds
- Remove BF MYLAR - semi-hot

SIZES

H 50 cm L 10 mt / 5mt / 2,5 mt

H 75 cm /

H 100 cm /

H 150 cm /

Oeko-Tex
Standard 100
Class I



Comply with
regulation REACH
n°1907/2006/EU

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications. Rev_2021/03

TECHNICAL DATA



Film: PU/polyurethane



Thickness: 170μ (±5%)



Liner: adhesive PET



Finish: opaque



Inks: solvent, eco-solvent, latex

PLOTTER SETTING



Cut settings: do not mirror



Blade: 45°



Minimum cut: 1 cm

APPLICATION



Temperature: 145°C - 295°F



Time: 12''



Liner removal: semi-hot,
wait 6/7 seconds



Pressure: medium - 3,5 bar - 50 PSI



Textile: organic, synthetic, mixed

WASH RESISTANCE

First wash after application

wait 12 hours

Max wash temperature*

40°C - 104°F

Dry clean



Dryer



*Temperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

BF PRINTOLD
PRINT&CUT



• *Vintage effect*